

# KAYU™ - Decking

## Density Comparison Guide

Wood/Source	LBS/CU FT	KG/M3
BATU (RB) – INDONESIA	60	960
MEMBATU (RB) – MALAYSIA	54	865
BANGKIRAI (YB) – INDONESIA	64	1020
KAPUR – INDONESIA	53	830
BUKIT (DRM) – MALAYSIA	53	830
IPE – BRAZIL	66	1050
CUMARU – BRAZIL	67	1070
WESTERN RED CEDAR – USA/CANADA	33	530
DOUGLAS FIR – USA/CANADA	48	770
REDWOOD – USA	40	640

### Sources:

- Malaysian Timber Industry Board
- Malaysian Timber Council
- Department of Forestry Indonesia
- International Tropical Timber Organization
- Center Technique Forestier Tropical
- US Department of Agriculture